



Fedtun Dry

DESCRIPTION: Self-drying mass.

USES INCLUDE: Tundish working lining.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

| | 65% | 75% | 85% |
|--------------------------------|------------|------------|------------|
| MgO | 65.0% | 75.0% | 85.0% |
| SiO ₂ | 22.0% | 15.0% | 8.0% |
| FeO | 3.0% | 3.0% | 1.5% |
| Al ₂ O ₃ | 2.0% | 2.5% | 1.5% |
| CaO | 2.0% | 3.0% | 3.5% |
| LOI | 0.5% | 0.5% | 0.5% |

TYPICAL AS RECEIVED PROPERTIES:

| | |
|--|-----------|
| Apparent Porosity (%): | 16.0 |
| Bulk Density, original (g/cm ³): | |
| @ 1000°C: | 1.8 - 2.1 |
| Working Temperature (°C): | 1670 |

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 24.04
