

INFORMATION BULLETIN

Fedvibe M

DESCRIPTION: Basic dry ramming material, which has good filling

and ramming properties. It has good low, intermediate, and high-temperature strength. It has

no offensive odor.

USES INCLUDE: Filler.

Patching. Leveling. Dry ramming.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

 $\begin{array}{ccc} \text{MgO} & 92.5\% \\ \text{SiO}_2 & 3.0\% \\ \text{CaO} & 2.0\% \\ \text{Fe}_2\text{O}_3 & 1.3\% \\ \text{Al}_2\text{O}_3 & 1.0\% \\ \end{array}$

TYPICAL AS RECEIVED PROPERTIES:

Bulk Density, pcf (g/cm^3): 125 (2.0)

Maximum Grain Size (mm): 4

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 24.01

Phone: 1-800-609-5711 www.FRCglobal.com