



Apex® 5

DESCRIPTION: Ladle and furnace brick, resin bonded, with high erosion and slag resistance. Antioxidants can be added.

USES INCLUDE: Electric furnace sidewalls.
Ladle barrels and bottoms.
BOF cones.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

MgO	94.9%
Fe ₂ O ₃	1.9%
CaO	1.0%
SiO ₂	1.0%
Al ₂ O ₃	0.2%

TYPICAL AS RECEIVED PROPERTIES:

Antioxidants:	Can be added
Apparent Porosity (%):	2.5
Bulk Density, original g/cm ³ (lb/ft ³):	3.00 (187)
Carbon (%)	5.0 - 20.0
Crushing Strength psi (MPa):	6000 (41)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
