



INFORMATION BULLETIN

Apex® 7HD

DESCRIPTION: Ladle and furnace brick, resin bonded, made with high-quality fused grain. Very high erosion and slag resistance. Good oxidation resistance due to high-purity flake graphite. Antioxidants can be added.

USES INCLUDE: Electric furnace hotspots.
Electric furnace sidewalls.
Ladles.
BOF working linings.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

MgO	97.5%
CaO	1.2%
Fe ₂ O ₃	0.6%
SiO ₂	0.6%
Al ₂ O ₃	0.2%

TYPICAL AS RECEIVED PROPERTIES:

Antioxidants:	Can be added
Apparent Porosity (%):	2.5
Bulk Density, original g/cm ³ :	3.50
Carbon (%):	5.0 – 20.0
Crushing Strength psi (MPa):	6000

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 23.07
