



Durachrome® FG20

DESCRIPTION: Direct bonded magnesia-chrome brick. Fortified with fused magnesia-chrome grain for improved density and corrosion resistance.

USES INCLUDE: Electric furnace roofs and sidewalls.
AODs.
Degassers.
Copper converters.
Lead smelters.
Nickel converters.
Ladle working and tank linings.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

MgO	61.0%
Cr ₂ O ₃	19.0%
Fe ₂ O ₃	12.0%
Al ₂ O ₃	6.8%
CaO	0.7%
SiO ₂	0.5%

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%):	15.0
Bulk Density, pcf (g/cm ³):	199 (3.18)
CCS psi (MPa):	7250 (50)
Hot MOR, 2700F psi (MPa):	290 (2)
RUL, ° F (° C):	> 3092 (1700)
Thermal conductivity, BTU/sf/hr2 (W/mk):	
400° F (200° C)	23.8
800° F (426° C)	22.2
1200° F (648° C)	21

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
