

INFORMATION BULLETIN

## Fedcast FG

## **DESCRIPTION:** Resin bonded castable made from fused magchrome grain.

**USES INCLUDE:** Sealing and filling the voids in walls and floors of basic brick linings.

## CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

MgO	65.2%
Cr <sub>2</sub> O <sub>3</sub>	19%
Fe <sub>2</sub> O <sub>3</sub>	5.7%
Al <sub>2</sub> O <sub>3</sub>	4.1%
SiO <sub>2</sub>	2.8%
CaO	0.7%

## TYPICAL AS RECEIVED PROPERTIES:

Temperature ° C (° F)	Bulk Density pcf (g/cc)	Cold Crushing Strength psi (MPa)	Porosity %
915 (1680)	192 (3.07)	2175 (15)	2765 (19)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11