



Flosan SDI

DESCRIPTION: Mixture of carefully selected and processed refractory materials with a high sintering point.

USES INCLUDE: Nozzle fill in sliding gate ladle systems.
E.B.T. furnace taphole.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

SiO ₂	35.0 - 40.0%
Cr ₂ O ₃	26.0 - 30.0%
Al ₂ O ₃	8.0 - 12.0%
MgO	5.0 - 8.0%
Fe ₂ O ₃	0.7%
C	Yes

TYPICAL AS RECEIVED PROPERTIES:

Shipping: 3000 lb. super sacks
1000 lb. super sacks
50 lb. bags

Other packaging options may also be available.
Store pallets in a dry and protected area.

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 21.10
