



Paragon® PB6

DESCRIPTION: Carbon-bonded dolomite brick.

USES INCLUDE: Ladle working linings.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

CaO	55.0%
MgO	42.0%
Residual Carbon	6.0%
Fe ₂ O ₃	0.6%
SiO ₂	0.3%

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%):	4.0
Bulk Density, original (g/cm ³):	2.88
Crushing Strength (N/mm ²):	30

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
