



Apex 4

DESCRIPTION: Ladle and furnace brick, resin bonded, with good erosion and slag resistance. Antioxidants can be added.

USES INCLUDE: Electric furnace sidewalls
Ladle barrels and bottoms

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

MgO	94.9 %
CaO	1.3
SiO ₂	1.3
Fe ₂ O ₃	1.9
Al ₂ O ₃	1.0

TYPICAL AS RECEIVED PROPERTIES:

Bulk Density, Original g/cm ³ (lb/ft ³)	3.0 (187)
Crushing Strength psi (Mpa)	6000 (41)
Apparent Porosity %	~ 3
Anti-Oxidants	Can be added
% Carbon:	5 - 20

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11
