



Atlas 95: Burned Magnesite Brick

DESCRIPTION: Atlas 95 (with or without tar impregnation- TI)

USES INCLUDE: EAF sub-hearth. BOF and ladle safety lining

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % - calcined basis)

MgO	95 %
CaO	1.4 %
Silica	1.6 %
Fe ₂ O ₃	1.1 %
Al ₂ O ₃	0.7 %

TYPICAL AS RECEIVED PROPERTIES:

Bulk Density g/cm ³ (pcf)	2.94 (183)
Cold Crushing Strength Mpa (psi)	100 (14500)
Apparent Porosity %	< 18 (before impregnation)
Modulus of rupture Mpa (psi)	
@22°C	15 (2175)
@1482°C	3 (435)
Refractoriness under load, °C (°F)	1620 (2948)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11
