



Durachrome® FG20

DESCRIPTION: Direct-bonded magnesia-chrome brick. Fortified with fused magnesia-chrome grain for improved density and corrosion resistance.

USES INCLUDE: Electric furnace roofs and sidewalls
AODs
Degassers
Copper Converters
Lead Smelters
Nickel Converters
Ladle Working and Tank Linings

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

MgO	61.0
Cr ₂ O ₃	19.0
SiO ₂	0.5
Al ₂ O ₃	6.8
Fe ₂ O ₃	12.0
CaO	0.7

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity %	15.0
Bulk Density, pcf (g/cm ³)	199(3.18)
CCS, psi (Mpa)	7250(50)
HMOR, 2700F psi (Mpa)	290(2)
RUL, °F(°C)	>3092(1700)
Thermal conductivity, BTU/sf/hr ² (W/MK)	
400°F(200°C)	23.8
800°F(426°C)	22.2
1200°F(648°C)	21

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11