



## Durachrome® FG95

---

**DESCRIPTION:** Magnesia-chrome brick, fired, made with predominately fused magnesite-chrome grain. Very high erosion and slag resistance with excellent resistance to thermal cycling. Low residuals and higher chrome content than standard for higher wear areas like tuyeres, slag lines and snorkels.

**USES INCLUDE:** Electric furnace roofs and sidewalls  
AODs  
Degassers  
Copper Converters  
Lead Smelters  
Nickel Converters  
Ladle Working and Tank Linings

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

MgO	≥60 % by weight (approx.)
Cr <sub>2</sub> O <sub>3</sub>	≥20 %
CaO	<2 %
SiO <sub>2</sub>	<2 %
Fe <sub>2</sub> O <sub>3</sub>	<8 %
Al <sub>2</sub> O <sub>3</sub>	<4 %

### TYPICAL AS RECEIVED PROPERTIES:

Bulk Density, pcf (g/cm <sup>3</sup> )	203(3.26)
Apparent Porosity	15 %
CCS, psi(Mpa)	11600(80)
HMOR, 2700F psi (Mpa)	580(4)
RUL, °F(°C)	>3092(1700)
Thermal conductivity, BTU/sf/hr <sup>2</sup> (W/MK)	
400°F(200°C)	34.6
800°F(426°C)	29.6
1200°F(648°C)	26.4

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11