



Epic® 80

DESCRIPTION: High alumina brick made from bauxite and high-purity clays

USES INCLUDE: Safety linings for ladles, working linings for ladles, tundishes, EAF roofs. Available with tar impregnation for iron ladle working linings (-TI).

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % - calcined basis)

Al ₂ O ₃	80.0 %
SiO ₂	16.6 %
TiO ₂	2.0 %
Fe ₂ O ₃	1.8 %
CaO	0.1 %
MgO	0.1 %
Alkalies	0.1 %

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity, %	19
Bulk Density, g/cm ³ (pcf)	2.80 (175)
Linear Reheat Expansion, %	+ 0.5
At 600° Thermal Conductivity, W/MK (btu/sf/hr2)	2.25 (15.6)
Cold Crushing Strength, MPa (psi)	70 (10150)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11
