



Fedgun 80

DESCRIPTION: Silicate-bonded magnesite gun mix for hot and cold maintenance

USES INCLUDE: Repair of basic linings in steel-making furnaces and ladles

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % - calcined basis)

MgO	80 %
CaO	7 %
SiO ₂	6.5 %
Fe ₂ O ₃	3.0 %

TYPICAL AS RECEIVED PROPERTIES:

Sizing:	0-3 mm
Packaging:	500 and 1000 kg sacks

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11
