



## FEDMOR 85

---

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

Al <sub>2</sub> O <sub>3</sub>	81.4%
SiO <sub>2</sub>	8.5 %
Fe <sub>2</sub> O <sub>3</sub>	1.1 %
TiO <sub>2</sub>	2.9%
CaO	0.1 %
MgO	0.1 %
Alkailes	0.1 %
P <sub>2</sub> O <sub>5</sub>	0.6 %

### TYPICAL AS RECEIVED PROPERTIES:

Modulus of Rupture (after drying):	>2.0MPA
PCE:	38

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11

---