



Fedplas 70

DESCRIPTION: Phos-bonded alumina plastic

USES INCLUDE: General repairs, linings of troughs, runners and spouts

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % - calcined basis)

Al ₂ O ₃	70 %
SiO ₂	24 %
Fe ₂ O ₃	0.8 %
TiO ₂	1.6 %
CaO	0.1 %
MgO	0.1 %
Alkalies	0.3 %

TYPICAL AS RECEIVED PROPERTIES:

Installed Bulk Density, pcf (g/cc)	169 (2.70)
------------------------------------	------------

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11
