



Flosan® GDS

DESCRIPTION: Flosan® GDS is a mixture of carefully selected and processed refractory materials with a high sintering point. The product is used as nozzle fill in sliding gate ladle systems, and can also be used in E.B.T. furnace taphole.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

Cr ₂ O ₃	32 - 36 %
MgO	6 - 9 %
Al ₂ O ₃	9 - 13 %
SiO ₂	26 - 30 %
C	Yes
Fe ₂ O ₃	15 – 19 %

PACKAGING AND STORAGE:

Shipped in either 3000 lbs. super sacks, 1000 lb. drums, 50 lb. bags, or 25 lb. bags. Other packaging options may also be available. Store pallets in a dry and protected area.

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11