



## Flosan®

---

**DESCRIPTION:** Flosan® is a mixture of carefully selected and processed refractory materials with a high sintering point. The product is used as nozzle fill in sliding gates ladle system and also in E.B.T. furnace taphole.

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

Cr <sub>2</sub> O <sub>3</sub>	34 - 38 %
MgO	7 - 10 %
Al <sub>2</sub> O <sub>3</sub>	10 - 14 %
SiO <sub>2</sub>	22 - 26 %
C	Yes
Fe <sub>2</sub> O <sub>3</sub>	16 - 20 %

### PACKAGING AND STORAGE:

Shipped in either 3000 lbs. super sacks, 1000 lb. drums, 50 lb. bags, or 25 lb. bags. Other packaging options may also be available. Store pallets in a dry and protected area.

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11

---