



Icon

DESCRIPTION: Magnesia Alumina Carbon

USES INCLUDE: Ladle barrels and bottoms

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

Al ₂ O ₃	10 %
MgO	78 %
C	7 %

TYPICAL AS RECEIVED PROPERTIES:

Bulk Density, original g/cm ³	3.00
Cold Crushing Strength psi	> 8000
Apparent Porosity %	< 5

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11
