



## Jefrit 85

---

**DESCRIPTION:** Jefrit 85 is repair mix, used for hot repair of EOP lining, produced from DBM.

**USES INCLUDE:** Repair mix

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

MgO	83.0 % min, 85.0% typ
CaO	7.0 %
Fe <sub>2</sub> O <sub>3</sub>	7.8 %
SiO <sub>2</sub>	1.5 %

### TYPICAL AS RECEIVED PROPERTIES:

Grain size	0-8 mm
Application method	throwing
Bonding type	ceramic
Temp. limit for application	1750 °C
Storage limit	6 months

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11

---