



Oracle

DESCRIPTION: Resin-bonded alumina-magnesia-carbon brick made from high-purity materials with anti-oxidants standard

USES INCLUDE: Ladle working linings

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

	Oracle	Oracle IP	Oracle HP
Al ₂ O ₃	78	80	84
SiO ₂	7	5	1
MgO	10	10	10
C	5	5	5

TYPICAL AS RECEIVED PROPERTIES:

Bulk Density, g/cm ³ (pcf)	2.90 (181)	3.20 (200)	3.15 (197)
Cold Crushing Strength, MPa (psi)	8000 (55)	12000 (82)	9000 (62)
Apparent Porosity, %	5	4	4

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11
