



Paragon PB

DESCRIPTION: Carbon-bonded dolomite brick

USES INCLUDE: Ladle working linings

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % - calcined basis)

MgO	40 %
CaO	60 %
SiO ₂	0.5 %
Fe ₂ O ₃	0.6 %
Residual carbon	2.2 %

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity %	4
Bulk Density g/cm ³	2.93
Cold Crushing Strength n/mm ²	40

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11
