



Paragon PB6

DESCRIPTION: Carbon-bonded dolomite brick

USES INCLUDE: Ladle working linings

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

MgO	42 %
CaO	55 %
SiO ₂	0.3 %
Fe ₂ O ₃	0.6 %
Residual Carbon	6 %

TYPICAL AS RECEIVED PROPERTIES:

Bulk Density, Original:	2.88 g/cm ³
Crushing Strength:	30 N/mm ²
Apparent Porosity:	4 %

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.11