



INFORMATION BULLETIN

Paragon® RDM6

DESCRIPTION: Dolomite brick with resin bonded and graphite.

USES INCLUDE: Ladle brick material.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

| | |
|--------------------------------|-------|
| MgO | 55.0% |
| CaO | 43.0% |
| Residual Carbon | 6.0% |
| SiO ₂ | 0.6% |
| Fe ₂ O ₃ | 0.5% |

TYPICAL AS RECEIVED PROPERTIES:

| | |
|--|------|
| Bulk Density (g/cm ³): | 2.88 |
| Cold Crushing Strength (N/mm ²): | 70 |
| Required Material (kg/dm ³): | 4.0% |

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 24.01
