



Fedmor 85

DESCRIPTION:

USES INCLUDE:

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

Al ₂ O ₃	81.4%
SiO ₂	8.5%
TiO ₂	2.9%
Fe ₂ O ₃	1.1%
P ₂ O ₅	0.6%
Alkalis	0.1%
CaO	0.1%
MgO	0.1%

TYPICAL AS RECEIVED PROPERTIES:

MOR after drying (MPa):	> 2.0
PCE:	38

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
