



## Fedmor 90P

---

**DESCRIPTION:** Chemically bonded, high-temperature thick mortar for use in refractory applications.

**USES INCLUDE:** General construction and maintenance of refractory linings of all kinds.

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

Al <sub>2</sub> O <sub>3</sub>	90.0 - 91.0%
P <sub>2</sub> O <sub>5</sub>	4.0 - 5.0%
SiO <sub>2</sub>	< 4.0%
Na <sub>2</sub> O + K <sub>2</sub> O	< 0.5%
Other	< 0.5%
Fe <sub>2</sub> O <sub>3</sub>	< 0.25%

### TYPICAL AS RECEIVED PROPERTIES:

Bulk Density (C865) g/cc (lb./ft <sup>3</sup> ):	
24°C (75°F)	2.55 - 2.65 (159 - 165)
816°C (1500°F)	2.25 - 2.35 (140 - 147)
Maximum Grain Size mm (mesh):	1.4 (14)
Maximum Hot Face Temperature:	
°C (°F)	1760 (3200)
Wet Material Required for Use:	
Kg/m <sup>3</sup> (lb./ft <sup>3</sup> )	2565 - 2645 (160 - 165)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11

---