



Fedtun Dry

DESCRIPTION: Self-drying mass.

USES INCLUDE: Tundish working lining.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

	65%	75%	85%
MgO	65.0%	75.0%	85.0%
SiO ₂	22.0%	15.0%	8.0%
FeO	3.0%	3.0%	1.5%
Al ₂ O ₃	2.0%	2.5%	1.5%
CaO	2.0%	3.0%	3.5%
LOI	0.5%	0.5%	0.5%

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%):	16.0
Bulk Density, original (g/cm ³):	
@ 1000°C:	1.8 – 2.1
Working Temperature (°C):	1670

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 24.04