



## Flosan<sup>®</sup> Q - I

---

**DESCRIPTION:** High chromite mixture of carefully selected and processed refractory materials with a high sintering point. Made with high-purity zircon.

**USES INCLUDE:** Nozzle fill in sliding gate ladle systems.

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

Cr <sub>2</sub> O <sub>3</sub>	32.0 - 38.0%
Zircon	17.0 - 23.0%
Fe <sub>2</sub> O <sub>3</sub>	16.0 - 21.0%
Al <sub>2</sub> O <sub>3</sub>	8.0 - 12.0%
MgO	6.0 - 9.0%
SiO <sub>2</sub>	4.0 - 8.0%
C	yes

### TYPICAL AS RECEIVED PROPERTIES:

Shipped in either 1400 kg super sacks (approx. 3086 lb.), 1000 lb. drums, or 50 lb. bags. Other packaging options may also be available. Store pallets in a dry and protected area.

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 21.10

---