



Jehearth 358

DESCRIPTION: Made from dead burnt alpine magnesite clinker with a high bulk density and improved lime/silica ratio. Strictly specified granulometry curves and composition ensure a high-density rammed monolithic layer. The ramming mix is delivered in a “ready to use” condition, with the possibility of oil treatment to control dust.

USES INCLUDE: The first installation of a new monolithic bottom.
Repairs of EAF bottoms.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

MgO	78.0%
CaO	12.0%
Fe ₂ O ₃	6.0%
SiO ₂	1.0%
Al ₂ O ₃	0.3%

TYPICAL AS RECEIVED PROPERTIES:

Bond	Ceramic
Bulk Density (kg/cm ³):	2.7
Grain Size (mm):	0 – 8

Shipped in 500 kg bags, 1500 kg bags, or 2000 kg bags.
Store pallets in a dry and protected area.

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
